



(11)

EP 1 157 974 A1

(12)

EUROPEAN PATENT APPLICATION

(43)

Date of publication:
28.11.2001 Bulletin 2001/48

(51)

Int Cl.7: C03C 13/00

(21)

Application number: 01119722.5

(22)

Date of filing: 08.11.1995

<div><div>(84)</div><div>Designated Contracting States: AT BE CH DE DK ES FR GB GR IT LI NL SE Designated Extension States: LT LV SI</div></div> <div><div>(30)</div><div>Priority: 08.11.1994 GB 9422468 23.11.1994 GB 9424126 23.11.1994 GB 9424127 13.01.1995 GB 9500667</div></div> <div><div>(62)</div><div>Document number(s) of the earlier application(s) in accordance with Art. 76 EPC: 97107510.6 / 0 792 844 95937881.1 / 0 790 962</div></div> <div><div>(71)</div><div>Applicant: Rockwool International A/S DK-2640 Hedehusene (DK)</div></div>	<div><div>(72)</div><div>Inventors:<ul style="list-style-type: none">Jensen, Soren Lund 1055 Kobenhavn K (DK)Guldborg, Marianne 2860 Soborg (DK)Christensen, Vermund Rust 4000 Roskilde (DK)</div></div> <div><div>(74)</div><div>Representative: Lawrence, Peter Robin Broughton et al GILL JENNINGS & EVERY, Broadgate House, 7 Eldon Street London EC2M 7LH (GB)</div></div> <div><div>Remarks:</div><div>This application was filed on 27 - 08 - 2001 as a divisional application to the application mentioned under INID code 62.</div></div>
--	--

(54)

Man-made vitreous fibres

(57)

Man-made vitreous fibres have a melt viscosity
of 10-70 poise at 1,400°C and an Al₂O₃ content of 16

to 30% by weight (measured as oxides) and are used
as biodegradable fibres. Novel fibres contain at least 6%
by weight Na₂O + K₂O.

Description

[0001] This invention relates to man-made vitreous fibres (MMVF) which are durable in use but which can be shown to be biologically advantageous.

[0002] MMV fibres are made from vitreous melt, such as of rock, slag, glass or other mineral melts. The melt is formed by melting in a furnace a mineral composition having the desired analysis. This composition is generally formed by blending rocks or minerals to give the desired analysis. The mineral composition often has an analysis, as oxides, which includes at least 32% SiO₂, below 30% Al₂O₃ and at least 10% CaO. The elemental analyses in the specification are by weight and calculated as oxides. The iron oxide may be a mixture of FeO and Fe₂O₃ but is quoted herein as FeO.

[0003] Efficient and cost-effective formation of the melt in the furnace and of the fibres from the melt requires that the composition should have a suitable liquidus temperature and should have a suitable viscosity during the fibre-forming process. These requirements impose constraints on the selection of the composition that is to be melted.

[0004] Although there is no scientific evidence establishing that there is a health risk associated with the manufacture and use of MMV fibres, commercial interests have led manufacturers to provide MMV fibres that retain the required physical properties of MMV fibres (e.g., durability at elevated temperatures and under humid conditions) but which can also be alleged to be of improved biological safety.

[0005] This allegation of improved safety is usually made on the basis of an in vitro test that examines the dissolution rate or degradability of the fibres in a liquid which is intended to simulate lung liquid, such as Gamble's solution with pH 7.4 to 7.8. A consequence of enhanced dissolution rate at pH 7.5 is that the fibres will normally have reduced resistance to humidity.

[0006] Numerous patent applications have been published describing fibres that give enhanced dissolution rate in such an in vitro test, such as WO87/05007, WO89/12032, EP 412878, EP459897, WO92/09536, WO93/22251 and WO94/14717.

[0007] A characteristic of many of these patent applications, and of fibres which are alleged to have enhanced dissolution rate in such in vitro tests, is that the fibre should have reduced aluminium content. For instance it is stated in WO87/05007 that the Al₂O₃ amount must be below 10%. The aluminium content of rock wool and slag wool is generally in the range 5 to 15% (measured as Al₂O₃ by weight) and many of these allegedly biologically suitable fibres have an aluminium content of below 4%, and often below 2%. It is known to include phosphorous in these low-Al₂O₃ compositions in order to increase the dissolution rate in this pH 7.5 dissolution rate test.

[0008] A problem with many of these low-Al₂O₃ fibres (in addition to uncertainty as to whether they do have enhanced biological suitability) is that the melt properties are not entirely satisfactory for manufacture in conventional or easily adapted melting and fibre-forming apparatus. For instance the melt viscosity at convenient fibre-forming temperatures may be rather low. Another problem is that a high dissolution rate at pH 7.5 may tend to result in reduced durability under humid conditions which may be experienced after installation.

[0009] In addition to the in vitro tests, in vivo research testing has been conducted. For instance Oberdörster in VDI Berichte 853, 1991, pages 17 to 37 showed that two basic mechanisms are involved in the clearance of fibres from the lungs, namely dissolution in the near-neutral lung fluid and dissolution in the acidic environment (maintained at pH 4.5 to 5) created around fibres surrounded by macrophages in the lung. It is believed macrophages promote removal of the fibres from the lung by promoting local dissolution of the surrounded fibre area leading to weakening and breaking of the fibres so as to reduce the average fibre length, thereby enabling macrophages to engulf and transport the shorter fibres out of the lung. This mechanism is illustrated in the article by Morimoto et al in Occup. Environ. Med 1994, 51, 62-67 and especially Figures 3 and 7 and articles by Luoto et al in Environmental Research 66 (1994) 198-207 and Staub-Reinhalung der Luft 52 (1992) 419-423.

[0010] Traditional glass fibres and many of the MMV fibres claimed to have increased solubility in lung fluid (at pH 7.5) have a worse solubility at pH 4.5 than at pH 7.5 and so presumably attack by macrophages would not contribute significantly to the shortening and final removal of the fibres from the lung.

[0011] Existing MMV fibres formed from rock, slag and other relatively high alkaline earth mixtures can have a higher dissolution rate at pH 4.5 than pH 7.5 but tend to have a low melt viscosity. Existing fibres which are promoted as being biologically acceptable do not have a satisfactory combination of dissolution rate at pH 4.5 with melt properties. Fibres which are currently alleged to be preferred on the basis of in vitro tests tend to have low melt viscosity when they have the required low aluminium content. The low melt viscosity inevitably reduces production efficiency compared to normal production.

[0012] It would be desirable to provide MMV fibres which can be shown to be biodegradable in the lung, have melt properties which allow for normal, high, production efficiency and which can be made from inexpensive raw materials. Preferably they have good weathering resistance when exposed to ambient humid conditions in use.

[0013] In the invention we use, as fibres having satisfactory biological solubility, fibres which have a dissolution rate measured at pH 4 to 5 of at least 20nm per day and which are formed of a composition having a melt viscosity at 1,400°C of 10-70 poise. For instance the dissolution rate at pH 4.5 can be at least 30 or even at least 50 nm per day

or more.

[0014] The combination of the melt viscosity and the solubility at pH 4.5 means that we can use a melt which is convenient to fiberise by conventional techniques and can produce fibres which are biologically soluble at pH 4.5. It is new to formulate or select fibres according to this combination, and many such fibres have a novel composition.

[0015] In a preferred aspect of the invention we determine the melt viscosity and the fibre dissolution rate at a pH in the range 4-5 of one or more compositions, we select a composition which has a melt viscosity at 1400°C of 10 to 70 poise and provides fibres which have a dissolution rate at pH 4.5 of at least 20nm per day and which has an analysis, measured as weight of oxides, which includes

SiO ₂	32 to 48%
Al ₂ O ₃	10 to 30%
CaO	10 to 30%
MgO	2 to 20%
FeO	2 to 15%
Na ₂ O + K ₂ O	0 to 12%
TiO ₂	0 to 6%
Other Elements	0 to 15%

and we make fibres from this composition.

[0016] It is surprisingly possible, in accordance with the invention, to provide fibres which have a good dissolution rate at pH 4.5 thereby facilitating clearance from the lungs by macrophages (thus promoting genuine biodegradability), even though the fibres can have low or moderate dissolution rate at pH 7.5. This allows maintenance of good stability under humid conditions (without loss of biodegradability). The fibres can have reasonably conventional melt characteristics such as liquidus temperature, crystallisation rate and melt viscosity. The fibres can be formed using inexpensive raw materials.

[0017] Another advantage of the fibres is that when they are exposed to humidity and condensed water, the resultant solution that is formed containing dissolution products has increased pH but the fibres may have reduced solubility at increased pH and so they may dissolve less and have increased durability.

[0018] The invention broadly includes all MMVF products made from a composition having the melt viscosity at 1,400°C of 10-70 poise and wherein the manufacture, promotion or sale or use involves measurement of, or reference to measurement of, solubility at about pH 4.5 (e.g., 4 to 5) and/or in the environment of macrophages in the lung irrespective of whether the dissolution rate is measured during the actual production of such products. The fibres preferably have an analysis as stated above.

[0019] The invention includes the use of the stated composition to promote the removal of MMVF fibres from human lungs. The invention also includes the use of the stated fibres to impart the ability to be rejected from human lungs.

[0020] The invention includes MMVF products, including MMV fibres, made from a composition which has been selected in order to provide the stated solubility. For instance it includes the measurement of pH 4-5 solubility and the melt viscosity of one or more compositions and selecting a composition partly or wholly on the basis of observing melt viscosity and solubility value at pH 4-5, and utilising compositions having the same or substantially the same analysis for making MMVF products. Any deviations in the analysis must be sufficiently small that they do not significantly alter the pH 4-5 solubility. When conducting the measurements to allow a selection of fibres to be made, the solubility can be determined at any pH (usually in the range 4-5) which correlates to the pH at 4.5. The melt viscosity can be determined either by deduction from data or by measurement and/or calculation, for any temperature (usually in the range 1,370-1,450°C) which gives a value which correlates with the value at 1,400°C.

[0021] The selection of the composition does not have to be conducted at the same location or at about the same time as carrying out the commercial production using the selected composition. Thus a manufacturer may conduct tests, or sponsor others to conduct tests, to determine solubility and use the information from these tests as part of the basis for selecting the composition which is used for making the fibres commercially.

[0022] The invention includes products having the quoted analysis and are formed from a composition having the quoted melt viscosity and which are labelled or sold as having the defined dissolution rate at pH 4-5. The invention includes packages which contain MMV fibres and which carry a label or insert, or which are sold with advertising, which refers to solubility at pH in the range 4-5 or in the environment of macrophages or which refers to a test method which measures such solubility.

[0023] The invention includes novel MVVF products. These include horticultural MMVF growth media and fibre reinforcement wherein the fibres are as defined in the invention.

[0024] One class of fibres which are novel are fibres having the solubility, melt viscosity and composition analysis given above except that the amount of Al₂O₃ is at least 18%. Other useful fibres have Al₂O₃ above 16%. Often it is

above 19 or 20%, for instance up to 26 or 28%. In fibres having Al_2O_3 above 16% the combined amount of alkali ($\text{Na}_2\text{O} + \text{K}_2\text{O}$) is usually at least 1% and preferably at least 2%, up to 7% or 10% or more. The amount of alkali is usually below 5% and preferably below 3% when the amount of Al_2O_3 is above 16%. These fibres can have good fire resistance and other mechanical properties. When these properties are of less importance, fibres having useful pH 4.5 solubility can be obtained with amounts of Al_2O_3 below 16% and amounts of $\text{Na}_2\text{O} + \text{K}_2\text{O}$ above 6 or 7%, for instance 8 to 12%, usually 8-10%.

[0025] Another class of fibres which are novel are fibres which preferably have the solubility and melt viscosity given above and which have the general analysis given above except that the alkali ($\text{Na}_2\text{O} + \text{K}_2\text{O}$) is above 6% and the amount of Al_2O_3 is usually 12-18%, and is often not more than 16% preferably 13-16%. Often the composition contains 0.5-4% TiO_2 , usually 1-2% TiO_2 . The alkali is usually provided by at least 5% and often at least 7%, Na_2O . The total amount of alkali ($\text{Na}_2\text{O} + \text{K}_2\text{O}$) is preferably 8-12%, often 8-10%.

[0026] It is possible to select elemental analyses within the general ranges given above so as to obtain the defined combination of melt viscosity and dissolution rate at pH 4.5. Also, it is easily possible to select the composition such that the composition and the fibres comply with other desirable properties, such as liquidus temperature and sintering temperature.

[0027] For instance, if it is found that the viscosity at 1400°C of any particular melt is too high, it may be possible to reduce it by reducing the total amount of $\text{SiO}_2 + \text{Al}_2\text{O}_3$. Similarly, if the melt viscosity is too low, it may be possible to increase it by raising the total amount of $\text{SiO}_2 + \text{Al}_2\text{O}_3$, generally within the range of 55 to 75%, often 60 to 75%, or by increasing the amount of alkali oxide. Similarly, it may be possible to decrease the viscosity by increasing the total amount of alkaline earth metal oxide components and FeO.

[0028] If the rate of dissolution at pH 4.5 is too low it may be possible to increase it by decreasing the amount of SiO_2 , but it may then be necessary to increase the amount of Al_2O_3 (and/or to add a component such as P_2O_5) in order to maintain melt properties.

[0029] The amount of SiO_2 is normally at least 32%, often at least 34% and preferably at least 35%. It is normally below 47% and preferably below 45% and is often 38-42%. However amounts of 42 to 47% are preferred when the amount of Al_2O_3 is not more than 16%.

[0030] The amount of Al_2O_3 is normally at least 12% and preferably at least 13%. When the amount of alkali is relatively low, good solubility at pH 4.5 can be obtained with Al_2O_3 amounts above 16 or 17%, especially at least 18%, but preferably at least 20% and often at least 24%. It is normally below 28% and preferably below 26%. Amounts of 20-23% are often preferred. However when the amount of alkali is relatively high (for instance at least 7% $\text{Na}_2\text{O} + \text{K}_2\text{O}$) good solubility at pH 4.5 can be obtained with Al_2O_3 amounts below 16%, eg 13-15%.

[0031] The combined amount of $\text{SiO}_2 + \text{Al}_2\text{O}_3$ is normally 55 to 75%, usually at least 56% and preferably at least 57%. In preferred products it is often above 60%, most preferably at least 61 or 62%. It is normally below 70% or 68% and preferably below 65%. When the amount of Al_2O_3 is not more than 16%, the amount of $\text{SiO}_2 + \text{Al}_2\text{O}_3$ is often 56-60%.

[0032] The amount of CaO is normally at least 14% and preferably at least 18%. It is normally below 28% and preferably below 25%. Amounts of 14-20% are often preferred.

[0033] The amount of MgO is normally at least 5%, preferably at least 6% and most preferably at least 8%. It is normally below 15%, preferably below 11%. When the amount of Al_2O_3 is not more than 16%, the amount is preferably 5-11%.

[0034] The amount of FeO is normally at least 3% and preferably at least 5%. It is normally below 12%, preferably below 10% and most preferably below 8%. Amounts of 5-7% are often preferred. Preferably $\text{CaO} + \text{MgO} + \text{FeO}$ is 25 to 40%.

[0035] The composition often includes TiO_2 in an amount of up to 3% or 4%, usually up to 2%. The amount of TiO_2 is usually at least 0.2%, often at least 0.5 or 1%.

[0036] A variety of other elements can be present in the composition in any amount that does not detract from the desired properties. Examples of other elements that can be included are P_2O_5 , B_2O_3 , BaO, ZrO_2 , MnO, ZnO and V_2O_5 .

[0037] It is often desirable to include P_2O_5 and/or B_2O_3 for instance to adjust melt properties or to adjust solubility. The total amount of P_2O_5 and B_2O_3 is generally not more than 10%. The amount of P_2O_5 is usually more than the amount of B_2O_3 and is usually at least 1% or 2%. Often B_2O_3 is absent. Preferably there is 1 to 8%, usually 1 to 5%, P_2O_5 and 0 to 5% B_2O_3 (often 1 to 4% B_2O_3).

[0038] The total amount of these various other elements is usually below 15% and often below 10% or 8%. Each of the other elements which is present is normally present in an amount of not more than 2%, except than P_2O_5 and/or B_2O_3 may be present in larger amounts as mentioned above.

[0039] The melt can have normal crystallisation characteristics, but when it is desired to minimise crystallisation this can be achieved by including magnesium in a rather low amount for instance 2 to 6% MgO.

[0040] When it is desired to provide fibres having improved fire resistance, it is generally desired to increase the amount of FeO, which preferably is then at least 6%, for instance up to 8% or higher, for instance 10%, and the MgO should then be at least 8%.

[0041] The analysis of the composition is preferably such that the fibres have a dissolution rate at pH 4.5 of at least 25, and preferably at least 40, nm per day. It is desirable for the dissolution rate to be as high as possible (consistent with retention of adequate humidity and heat resistance properties) but it is generally unnecessary for it to be above 150 or 100nm per day and it is usually below 80nm per day.

[0042] Although a high dissolution rate at pH 7.5 has been proposed as a desirable property (as an indication of alleged biodegradability), in fact it is often an undesirable property since it is an indication of poor weathering resistance when exposed to humidity. Dissolution in the lungs at pH 7.5 is not exclusively necessary for the fibres to be biodegradable. Preferably the fibres have a dissolution rate in Gambles solution at pH 7.5 of below 25, and most preferably below 15, nm per day.

[0043] The viscosity of the composition at 1400°C is usually at least 12 or 15 poise and is preferably at least 18 poise. Although it can be as high as, for instance, 60 poise it is generally below 40 poise and preferably it is not more than 30 poise.

[0044] When it is desired that the fibres should have good fire resistance, the analysis is preferably such that the sintering temperature is at least 800°C and preferably at least 1,000°C.

[0045] The liquidus temperature is usually at least 1200°C but often at least 1240°C. It can be as high as, for instance, 1400°C but preferably it is not more than 1340°C.

[0046] An advantage of the use of the moderate aluminium melts defined for use in the invention is that it permits the inclusion in the composition of readily available materials having a moderate aluminium content such as rock, sand and waste. This therefore minimises the need to use expensive, high alumina materials such as bauxite or kaolin, and minimises at the same time the need to use expensive very low alumina materials such as silica sand or olivine sand, iron ore, etc. These more expensive materials may however be useful if desired. Typical, readily available, medium alumina materials that may be used as part or all of the composition include anorthosite and phonolite and gabbros.

[0047] The composition is typically formed by blending appropriate amounts of naturally occurring rock and sand materials such as anorthosite, gabbros, limestone, dolomite, diabase, apatite, boron-containing materials, and waste materials such as mineral wool waste, alumina silicates, slag, in particular high alumina (20-30%) slags such as ladle slag, foundry sand, filter dust, fly ash, bottom ash and high alumina waste from the production of refractory materials.

[0048] The composition can be converted to a melt in conventional manner, for instance in a gas heated furnace or in an electric furnace or in a cupola furnace. An advantage of the invention is that the composition can easily have a reasonably low liquidus temperature (while maintaining adequate viscosity at 1400°C) and this minimises the amount of energy that is required for forming the melt.

[0049] The melt can be converted to fibres in conventional manner, for instance by a spinning cup process or by a cascade rotor process, for instance as described in WO92/06047.

[0050] The fibres of the invention can have any convenient fibre diameter and length.

[0051] In this invention, dissolution rate is determined using the following test protocol.

[0052] 300mg of fibres are placed in polyethylene bottles containing 500ml of a modified Gamble's solution (i.e., with complexing agents), adjusted to pH 7.5 or 4.5, respectively. Once a day the pH is checked and if necessary adjusted by means of HCl.

[0053] The tests are carried out during a one week period. The bottles are kept in water bath at 37°C and shaken vigorously twice a day. Aliquots of the solution are taken out after one and four days and analysed for Si on a Perkin-Elmer Atomic Absorption Spectrophotometer.

[0054] The modified Gamble's solution has the following composition:

	g/l
MgCl ₂ .6H ₂ O	0.212
NaCl	7.120
CaCl ₂ .2H ₂ O	0.029
Na ₂ SO ₄	0.079
Na ₂ HPO ₄	0.148
NaHCO ₃	1.950
(Na ₂ -tartrate) .2H ₂ O	0.180
(Na ₃ -citrate) .2H ₂ O	0.152
90% lactic acid	0.156
Glycine	0.118
Na-pyruvate	0.172
Formalin	1 ml

[0055] The fibre diameter distribution is determined for each sample by measuring the diameter of at least 200 individual fibres by means of the intercept method and a scanning electron microscope or optical microscope (1000 x magnification). The readings are used for calculating the specific surface of the fibre samples, taking into account the density of the fibres.

[0056] Based on the dissolution of SiO_2 (network dissolution), the specific thickness dissolved was calculated and the rate of dissolution established (nm/day). The calculations are based on the SiO_2 content in the fibres, the specific surface and the dissolved amount of Si.

[0057] In this specification, the sintering temperature is determined by the following test protocol.

[0058] A sample (5 x 5 x 7.5 cm) of mineral wool made of the fibre composition to be tested is placed in a furnace preheated to 700°C. After 1.5 hours exposure the shrinkage and the sintering of the sample were evaluated. The method is repeated each time with a fresh sample and a furnace temperature 50°C above the previous furnace temperature until the maximum furnace temperature, at which no sintering or no excessive shrinkage of the sample is observed, was determined.

[0059] In this specification, the viscosity in poise at 1400°C is calculated according to Bottinga and Weill, American Journal of Science Volume 272, May 1972, page 455-475.

[0060] The following are examples of the invention.

[0061] Compositions were formed by blending appropriate proportions of raw materials as shown in the table and each was melted in a crucible furnace and was fiberised by the cascade spinner technique. The melt viscosity and solubility of each was determined. The analyses of the compositions and their properties are quoted in the following tables. In the invention, any of compositions A to X are judged to be suitable and are selected for the subsequent manufacture of MMVF products which are labelled as having good biological solubility. Those having viscosity above 20 and pH 4.5 solubility above 30 are preferred.

[0062] Product 1 is similar to, commercial slag wool and gives a poor viscosity. Product 2 is a high aluminium product but the proportions of all the components are such that the melt viscosity is too high for convenient spinning. Product 3 is similar to a conventional rock wool product with normal good product properties but has a very low dissolution rate at pH 4.5. Accordingly products 1, 2 and 3 are not selected for use in the manufacture of biologically soluble MMV fibre products.

Fibre Types	SiO ₂ %	Al ₂ O ₃ %	TiO ₂ %	FeO %	CaO %	MgO %	Na ₂ O %	K ₂ O %	SUH	Vis poise 1400°C	Diss rate pH 7.5 (st) nm/day	Diss rate pH 4.5 (st) nm/day	Sintering temp °C
A	34.5	28.0	1.8	3.3	25.4	5.6	0.6	0.8	100.0	21.2	9.5	34.8	>800
B	36.2	26.3	1.9	4.9	17.7	10.8	1.0	1.1	100.0	19.4	6.8	45.1	>800
C	38.3	25.0	1.7	3.0	24.9	5.6	0.7	0.8	100.0	24.7	7.4	53.8	>800
D	38.1	24.7	1.8	4.6	17.4	11.3	1.2	0.8	100.0	20.0	7.9	64.2	>800
E	43.2	20.0	1.6	5.0	16.6	11.5	1.2	0.8	100.0	22.8	5.0	57.9	>800
F	43.2	19.8	1.5	3.4	24.7	5.6	1.0	0.8	100.0	27.1	4.8	47.0	>800
G	47.7	19.4	0.8	3.7	16.6	10.8	0.4	0.4	100.0	34.7	3.0	21.0	>800
H	43.7	18.8	3.6	5.4	16.4	9.7	1.8	0.7	100.0	25.1	5.8	38.6	>800
I	45.6	18.1	1.5	5.3	16.5	9.7	2.5	0.7	100.0	30.8	3.1	44.4	>800
J	46.9	18.9	0.5	3.3	17.0	9.5	3.4	0.5	100.0	44.0	0.9	35.2	>800
K	44.1	18.7	1.6	5.2	16.5	9.8	3.3	0.7	100.0	30.3	2.6	41.1	>800
L	39.6	24.3	1.8	3.2	21.7	6.7	1.8	0.8	100.0	30.8	5.7	49	>800
M	43.8	20.4	1.2	10.3	15.6	8.3	0.2	0.3	100.0	21.9	3.9	39.7	>1000
N	42.9	23.2	0.7	8.8	17.5	5.1	0.6	1.4	100.0	36.8	-	45.9	>900
O	43.1	19.9	1.6	10.1	15.0	9.3	0.6	0.4	100.0	19.8	4.6	51.9	>1000
P	37.8	18.3	0.9	12.0	15.8	10.1	4.7	0.3	100.0	15.0	10.2	61.5	>1000
Q	40.0	22.2	2.0	7.5	15.2	10.7	1.5	0.8	100.0	19.4	7.1	61.1	>1000
R	45.4	14.5	1.6	5.6	15.3	7.2	9.0	0.9	100.0	39.9	3.1	48.1	>1000
S	45.3	17.5	1.1	5.7	20.3	7.8	1.7	0.6	100.0	25.9	1.8	48.6	>1000
T	43.1	14.0	0.7	0.5	34.3	5.2	0.7	1.5	100.0	15.2	1.5	59.8	>700
U	37.2	16.1	1.6	3.3	21.5	10.1	9.3	1.0	100.0	29.2	5.2	48.0	>800
V	42.9	16.6	1.7	6.4	16.8	9.6	5.2	0.8	100.0	25.3	3.1	21.9	>1000
W	38.9	16.4	1.4	8.4	20.0	7.9	6.4	0.6	100.0	20.2	9.5	33.0	>1000
X	42.5	16.4	1.7	5.8	21.1	6.3	5.4	0.8	100.0	27.1	4.1	32.9	>1000
1	42.7	8.8	0.3	0.4	36.9	9.4	0.7	0.3	100.0	8.2	13.9	41.1	>700
2	39.7	32.8	1.7	7.0	15.7	2.1	0.3	0.7	100.0	100.0	7.8	59.3	>1000
3	46.9	13.2	3.0	6.4	17.1	9.4	2.6	1.3	100.0	23.7	2.0	3.0	>1000

[0063] The selected fibres may be provided in any of the forms conventional for MMV fibres. Thus they may be provided as a product consisting of loose, unbonded fibres. More usually they are provided with a bonding agent, for instance as a result of forming the fibres and connecting them in conventional manner. Generally the product is consolidated as a slab, sheet or other shaped article.

[0064] Products according to the invention may be formulated for any of the conventional purposes of MMV fibres, for instance as slabs, sheets, tubes or other shaped products that are to serve as thermal insulation, fire insulation and protection or noise reduction and regulation, or in appropriate shapes for use as horticultural growing media, or as free fibres for reinforcement of cement, plastics or other products or as a filler.

Claims

1. Use as biodegradable man-made vitreous fibres of fibres formed of a composition which includes, by weight of oxides,

SiO ₂	32 to 48%
Al ₂ O ₃	16 to 30%
CaO	10 to 30%
MgO	2 to 20%
FeO	2 to 15%
Na ₂ O + K ₂ O	0 to 12%
TiO ₂	0 to 6%
Other Elements	0 to 15%

and the composition has a viscosity at 1400°C of 10 to 70 poise.

2. Use in mineral fibre products as biodegradable fibres of fibres formed of a composition which includes, by weight of oxides,

SiO ₂	32 to 48%
Al ₂ O ₃	16 to 30%
CaO	10 to 30%
MgO	2 to 20%
FeO	2 to 15%
Na ₂ O + K ₂ O	0 to 12%
TiO ₂	0 to 6%
Other Elements	0 to 15%

and the composition has a viscosity at 1400°C of 10 to 70 poise.

3. Use in mineral fibre products of man-made vitreous fibres which are shown to be biodegradable in the lung, wherein the fibres are formed of a composition which includes, by weight of oxides,

SiO ₂	32 to 48%
Al ₂ O ₃	16 to 30%
CaO	10 to 30%
MgO	2 to 20%
FeO	2 to 15%
Na ₂ O + K ₂ O	0 to 12%
TiO ₂	0 to 6%
Other Elements	0 to 15%

and the composition has a viscosity at 1400°C of 10 to 70 poise.

4. Use of fibres as biodegradable products, wherein the fibres are man-made vitreous fibres formed of a composition which includes, by weight of oxides,

SiO ₂	32 to 48%
Al ₂ O ₃	16 to 30%
CaO	10 to 30%
MgO	2 to 20%
FeO	2 to 15%
Na ₂ O + K ₂ O	0 to 12%
TiO ₂	0 to 6%
Other Elements	0 to 15%

and the composition has a viscosity at 1400°C of 10 to 70 poise.

5. A use according to any of claims 2 to 4 in which the product is a bonded product.
6. A use according to claim 5 in which the bonded product is used as thermal insulation, fire insulation or protection, noise regulation or protection, or as a horticultural growth medium.
7. Use according to any preceding claim in which the fibres are shown to be biodegradable in the lung by determination of solubility in the environment of macrophages in the lung.
8. Use according to any preceding claim in which the fibres have a dissolution rate as defined herein of at least 20nm per day calculated from the amount of Si in solution in modified Gambles solution at pH 4.5 after one day's immersion and after four day's immersion.
9. Use according to any preceding claim wherein the sintering temperature of the fibres in mineral wool formed from the fibres is at least 800°C.
10. Use according to any preceding claim in which the fibres have an analysis, measured as weight of oxides, which includes

SiO ₂	32 to below 45%
Al ₂ O ₃	above 16 to 28%
CaO	10 to 30%
MgO	2 to 20%
FeO	2 to 15%
Na ₂ O + K ₂ O	0 to 12%
TiO ₂	0 to 4%
Other Elements	0 to 8%

and the amount of SiO₂ + Al₂O₃ is below 68%.

11. Use according to any preceding claim in which the amount of magnesium expressed as MgO is at least 5% up to 20%.
12. Use according to any preceding claim in which the amount of iron, expressed as FeO, is below 10%.
13. Use according to any preceding claim in which the amount of iron, expressed as FeO, is above 5%.
14. Use according to any preceding claim in which the amount of aluminium, expressed as Al₂O₃ is at least 18%.
15. A use according to claim 14 in which the amount of Al₂O₃ is at least 20%.
16. A use according to claim 14 in which the amount of Al₂O₃ is 20 to 26%.

17. A use according to any preceding claim in which the amount of SiO_2 is below 42%
18. A use according to any preceding claim in which the amount of titanium, expressed as TiO_2 , is at least 0.5%.
- 5 19. A use according to any preceding claim in which the fibres have a dissolution rate at pH 7.5 below 15nm per day.
20. A use according to any preceding claim in which the composition provides a liquidus temperature of 1240 to 1340°C,
- 10 21. A product comprising man-made vitreous fibres formed of a composition having an analysis, as oxides, which includes

SiO_2	32 to 48%
Al_2O_3	10 to 18%
CaO	10 to 30%
MgO	2 to 20%
FeO	2 to 15%
$\text{Na}_2\text{O} + \text{K}_2\text{O}$	6 to 12%
TiO_2	0 to 6%
Other Elements	0 to 15%

and the composition has a viscosity at 1400°C of 10 to 70 poise,
and the fibres have a dissolution rate at pH 4.5 of at least 20nm per day.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 01 11 9722

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	FR 2 662 687 A (SAINT GOBAIN ISOVER) 6 December 1991 (1991-12-06) * page 5, line 25 - line 34; claims; examples; tables I,II *	1-21	C03C13/00
X	EP 0 459 897 A (SAINT GOBAIN ISOVER) 4 December 1991 (1991-12-04) * claims; examples *	1-21	
A	EP 0 231 691 A (SAINT GOBAIN ISOVER) 12 August 1987 (1987-08-12) * the whole document *	1-21	
A	GB 2 152 026 A (INST MINERAL ROHSTOFF LAGER) 31 July 1985 (1985-07-31) * the whole document *	1-21	
A	EP 0 583 791 A (SAINT GOBAIN ISOVER) 23 February 1994 (1994-02-23) * claim 27 *	1-21	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
			C03C
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 4 October 2001	Examiner Van Bommel, L
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03.82 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 11 9722

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

04-10-2001

Patent document cited in search report		Publication date		Patent family member(s)	Publication date
FR 2662687	A	06-12-1991	FR	2662687 A1	06-12-1991
			US	RE35557 E	08-07-1997
EP 0459897	A	04-12-1991	FR	2662688 A1	06-12-1991
			AT	121378 T	15-05-1995
			AU	642493 B2	21-10-1993
			AU	7731891 A	05-12-1991
			BR	9102232 A	07-01-1992
			CA	2043699 A1	02-12-1991
			CN	1059135 A , B	04-03-1992
			CS	9101625 A3	15-01-1992
			DE	69108981 D1	24-05-1995
			DE	69108981 T2	07-12-1995
			DK	459897 T3	28-08-1995
			EP	0459897 A1	04-12-1991
			ES	2073136 T3	01-08-1995
			FI	912634 A	02-12-1991
			HR	940812 A1	30-04-1997
			HU	212280 B	29-04-1996
			IE	911846 A1	04-12-1991
			JP	3121374 B2	25-12-2000
			JP	4228455 A	18-08-1992
			KR	198907 B1	15-06-1999
			NO	912090 A	02-12-1991
			NZ	238315 A	25-02-1993
			PL	167825 B1	30-11-1995
			PT	97824 A , B	28-02-1992
			SI	9110957 A	30-04-1998
			SK	280187 B6	10-09-1999
			TR	28864 A	06-08-1997
			US	RE35557 E	08-07-1997
			US	5250488 A	05-10-1993
			ZA	9104026 A	25-03-1992
EP 0231691	A	12-08-1987	FR	2591423 A1	19-06-1987
			BR	8606226 A	29-09-1987
			DK	605086 A , B ,	18-06-1987
			EP	0231691 A1	12-08-1987
			ES	2031829 T3	01-01-1993
			IL	80982 A	23-12-1990
			JP	62148337 A	02-07-1987
			US	5037470 A	06-08-1991
			US	4867779 A	19-09-1989
			ZA	8609417 A	30-12-1987
GB 2152026	A	31-07-1985	DD	237434 A3	16-07-1986

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 01 11 9722

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

04-10-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
GB 2152026 A		DE 3438733 A1	11-07-1985
		IT 1178333 B	09-09-1987
		PL 251275 A1	27-08-1985
		SE 8406571 A	01-07-1985
EP 0583791 A	23-02-1994	CA 2121572 A1	03-03-1994
		WO 9404468 A1	03-03-1994
		AU 2433192 A	15-03-1994
		BR 9206653 A	24-10-1995
		CN 1087611 A	08-06-1994
		EP 0583791 A1	23-02-1994
		FI 941816 A	20-04-1994
		JP 7503696 T	20-04-1995
		NO 941403 A	18-04-1994
		NZ 248380 A	21-12-1995
		SI 9300437 A	31-03-1994
		SK 45594 A3	07-09-1994
		AU 668878 B2	23-05-1996
		HR 931148 A1	30-06-1996
		US 5554324 A	10-09-1996